

## TEST REPORT

# Libus Chile Spa

# Test Report

**SCOPE OF WORK**

Industrial Hard Hat Testing to ANSI/ISEA Z89.1-2014 (R2019), brand name Libus, model Milenium Class S/V Visor

**REPORT NUMBER**

105338672CRT-001

**ISSUE DATE**

September 20, 2023

**PAGES**

8

**DOCUMENT CONTROL NUMBER**

GFT-OP-10i (6-July-2017)

© 2023 INTERTEK



**TEST REPORT**

Libus Chile Spa  
Av. Francia 1314, Comuna  
Independencia Santiago  
Chile

Quote Number:	Qu-01388970-2
Reference Number/PO Number:	N/A
Certification Type:	Private
Product Type:	Industrial Hard Hat (ANSI)
Brand Name:	Libus
Model:	Milenium Class S/V Visor
Type (I or II):	Type I
Class (C,E, or G):	Class E
Suspension:	6 Pt. Ratchet
Optional Requirements:	N/A
Sample Control Number:	CRT2309111001-001
Sample Received Date:	9/11/2023
Number of Samples Received:	30
Condition received in:	Production Samples
Type of Testing Entity:	Third Party Testing Laboratory ANSI/ISEA Z89.1-2014 (R2019)
Test Standard:	American National Standard for Industrial Head Protection
Evaluation/Testing Location:	Intertek, 3933 US Rt. 11, Cortland NY 13045 Libus Chile Spa
Manufacturer's Name and Address:	Av. Francia 1314, Comuna Independencia Santiago Chile
Date(s) of Testing:	9/12/2023

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

## TEST REPORT

Dear Miguel,

Intertek has completed the evaluation of Industrial Hard Hat brand name Libus, model Milenium Class S/V Visor, to the following client specified clauses of ANSI/ISEA Z89.1-2014 (R2019). The evaluation was performed at Intertek located in Cortland, NY on the dates posted below. The results of these tests are as indicated below.

Test Completed	Test Date	ANSI/ISEA Z89.1-2014 (R2019) Clause	Pass/Fail
Instructions and Markings	9/12/2023	6	Pass
Flammability	9/12/2023	10.1	Pass
Force Transmission	9/12/2023	10.2	Pass
Apex Penetration	9/12/2023	10.3	Pass
Electrical Insulation	9/12/2023	10.7	Pass

This test report completes the testing covered by Proposal No. Qu-01388970-2. If there are any questions regarding the results contained in this report, or any of the other services offered by Intertek, please do not hesitate to contact the undersigned.

Please note: this Test Report does not represent authorization for the use of any Intertek certification marks.

Tested By,



Brandon Wood  
Technician

Reviewed by,



Jesse Lloyd  
Reviewer

REPORT REVISION		
Date	Revision Description	Reviewer
9/20/2023	Original report: 105338672CRT-001	Jesse Lloyd

## TEST REPORT

### Conditioning Requirements

Clause 8.3 & 8.5 (ANSI/ISEA Z89.1-2014 (R2019))

### Actual Conditions

	Required Temperature	Actual Temperature
Ambient Temperature	20°C to 26°C	21.5°C - 22.0°C
High Temperature	47°C to 51°C	49.7°C - 50.5°C
Low Temperature	-16°C to -20°C	-16.3°C - -18.0°C
Relative Humidity		46.0% - 47.0%

### Instructions and Marking Requirements

Clause 6 (ANSI/ISEA Z89.1-2014 (R2019))

Clause / Requirement	Pass/Fail
6.1 - Each helmet shall be accompanied by manufacturer's instructions explaining the proper method of size and adjustment, use, care, useful service life guidelines and, if applicable, reverse wearing.	Pass
6.2 - Each helmet shall bear permanent markings in at least 1.5 mm(0.06 in.) high letters stating the following information	
6.2a - Name or identification mark of the manufacturer	Pass
6.2b - The date of manufacturer	Pass
6.2c - The American National Standard Designation, ANSI/ISEA Z89.1 - 2014 (R2019)	Pass
6.2d - The applicable Type and Class Designations, followed by the optional criteria markings, if applicable	Pass
If optional criteria are applied, the appropriate markings shall follow the sequence as specified below	
Reverse Donning	N/A
LT - Lower Temperature	N/A
HT - Higher Temperature	N/A
HV - High Visibility	N/A

The test samples were marked with the following date code(s): 2/2023

## TEST REPORT

### Flammability

Clause 10.1 (ANSI/ISEA Z89.1-2014 (R2019))

Helmets shall be tested in accordance with Section 10.1 anywhere above the Static Test Line (STL). No flame shall be visible 5.0 seconds after the removal of the test flame.

Sample	Location	After flame (sec.)	Pass/Fail
12	Rear	0.0	Pass

### Force Transmission System Calibration - Pre Test

Clause 10.2.4 (ANSI/ISEA Z89.1-2014 (R2019))

Impactor Weight (lbs): 7.98  
Drop Height (in.): 8.25  
Peak g's 90 to 110

	Load Cell	Accelerometer	
Impact	Peak lbs.	Peak g	Peak g's Converted to lbs
1	807.66	102.46	817.63
2	810.23	102.88	820.98
3	810.20	102.95	821.54
4	807.43	102.66	819.23
5	810.95	102.62	818.91
Average	809.29	102.71	819.66
Percent Difference(< 2.5%)			1.28%

### Force Transmission Instrumentation Check

Clause 10.2.4 (ANSI/ISEA Z89.1-2014 (R2019))

Required Drop Height (in.): 33.5  
Required Velocity (m/s): 3.97 - 4.03

Pre Test		
Impact Number	Velocity (m/s)	Force (lbs.)
1	4.03	1989.54
2	4.00	1987.63
3	4.03	1989.54
Average Force (lbs.)		1988.90

Post Test		
Impact Number	Velocity (m/s)	Force (lbs.)
1	3.99	1989.08
2	3.99	1991.73
3	4.00	1998.16
Average Force (lbs.)		1992.99

Pre-Post Difference (<5%) 0.21%

**TEST REPORT**

**Force Transmission**

Clause 10.2 (ANSI/ISEA Z89.1-2014 (R2019))

Helmets shall be tested in accordance with Section 10.2 and shall not transmit a force to the test headform that exceeds 4450 N(1000lbs). Additionally, for each test condition specified, the maximum transmitted force of individual test samples shall be averaged. The averaged values shall not exceed 3780 N(850 lbs).

Velocity Range (m/s)	5.45 - 5.55
Actual Drop Height (in)	61
Impactor Mass (kg) (3.55kg - 3.65 Kg)	3.62

Hot Conditioning			
Sample	Velocity (m/s)	Force (lbs.)	Pass/Fail
1	5.50	399.12	Pass
2	5.56*	400.78	Pass
3	5.57*	409.53	Pass
4	5.55	412.69	Pass
5	5.49	393.78	Pass
6	5.55	389.57	Pass
7	5.57*	393.98	Pass
8	5.50	402.74	Pass
9	5.50	385.56	Pass
10	5.50	405.59	Pass
11	5.56*	394.29	Pass
12	5.56*	399.32	Pass
Average		398.91	Pass

Cold Conditioning			
Sample	Velocity (m/s)	Force (lbs.)	Pass/Fail
13	5.50	711.91	Pass
14	5.50	676.56	Pass
15	5.55	654.58	Pass
16	5.48	634.47	Pass
17	5.50	626.80	Pass
18	5.48	625.41	Pass
19	5.48	660.68	Pass
20	5.49	680.94	Pass
21	5.55	624.64	Pass
22	5.55	663.60	Pass
23	5.55	683.21	Pass
24	5.50	601.95	Pass
Average		653.73	Pass

Note: \*Over Standard velocity

## TEST REPORT

### Apex Penetration

Clause 10.3 (ANSI/ISEA Z89.1-2014 (R2019))

Helmets shall be tested in accordance with Section 10.3. The penetrator shall not make contact with the top of the test headform.

Velocity Range (m/s) 6.9- 7.1  
Headform Used: M  
Penetrator Mass (0.95Kg - 1.05Kg): 1.00

Hot Conditioning		
Sample	Velocity (m/s)	Pass/Fail
25	7.00	Pass
26	7.01	Pass
27	7.00	Pass

Cold Conditioning		
Sample	Velocity (m/s)	Pass/Fail
28	7.01	Pass
29	7.00	Pass
30	7.00	Pass

### Electrical Insulation

Clause 10.7 (ANSI/ISEA Z89.1-2014 (R2019))

Helmets shall be tested in accordance with Section 10.7.

For **Class E** helmets 20,000 Volts shall be applied for a duration of 3 minutes and the leakage(mA) shall not be greater than 9.0 mA. Then the voltage shall be increased to 30,000 Volts looking for burn through.

Sample	Leakage (mA)	Burn Through	Did Flashover Occur (Yes/No)	Pass/Fail
1	3.957	No	No	Pass
14	5.560	No	No	Pass

## TEST REPORT

### Measurement Uncertainty

Test	Relative MU (dMU)
Section 6 - Instructions and Markings	1.0%
Section 10.1 - Flammability	1.0%
Section 10.2 - Force Transmission	3.1%
Section 10.3 - Apex Penetration	3.4%
Section 10.7 - Electrical Insulation	0.0%
Section 10.8 - High Visibility	NA

### Sample Pictures

